

Customer No.: 31561  
Application No: 10/707, 112  
Docket NO.11761-US-PA

### Claim Amendment

Please amend the claims according to the following listing of claims and substitute it for all prior versions and listings of claims in the application.

1. (currently amended) A method of fabricating a passivation layer, comprising the steps of:
- providing a substrate having a plurality of device structures and at least an interconnect thereon;
  - forming a patterned metallic layer over the interconnect;
  - performing a plasma-enhanced chemical vapor deposition process to form a first passivation layer over the metallic layer, wherein the plasma-enhanced chemical vapor deposition process is carried out at a processing pressure between about 9-21 to 25 Torrs and with a processing power between about 1 to 45 Watts; and
  - forming a moisture impermeable second passivation layer over the first passivation layer.
- Claim 2 (cancelled)
3. (original) The method of claim 1, wherein the first passivation layer comprises a silicon oxide layer.
4. (original) The method of claim 1, wherein the second passivation layer comprises a silicon nitride layer.

2 BEST AVAILABLE CO

Customer No.: 31561  
Application No: 10/707, 112  
Docket NO.11761-US-PA

5. (currently amended) A method of fabricating a passivation layer, comprising the steps of:

providing a substrate having a plurality of device structures and at least an interconnect thereon;

forming a patterned metallic layer over the interconnect;

performing a semi-atmospheric chemical vapor deposition process with liquid tetra-ethyl-ortho-silicate (TEOS) and ozone inside a reaction chamber to form a first passivation layer over the metallic layer, wherein the liquid tetra-ethyl-ortho-silicate flowing into the reaction chamber has a flow rate between 500 sccm to 3000 sccm and the ozone flowing into the reaction chamber has a flow rate between 5000 sccm to 15000 sccm;  
and

forming a moisture impermeable second passivation layer over the first passivation layer.

Claims 6-7 (cancelled)

8. (original) The method of claim 5, wherein the pressure inside the reaction chamber during the semi-atmospheric chemical vapor deposition process is between about 20 to 750 Torr.

9. (original) The method of claim 5, wherein the semi-atmospheric chemical vapor deposition process is carried out at a temperature between about 200°C to 600°C.

Customer No.: 31561  
Application No: 10/707, 112  
Docket NO.11761-US-PA

10. (original) The method of claim 5, wherein the first passivation layer comprises a silicon oxide layer.

11. (original) The method of claim 5, wherein the second passivation layer comprises a silicon nitride layer.

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**